

CAPLAST-R/S

A WATER REDUCING & RETARDING CONCRETE ADMIXTURE

DESCRIPTION

CAPLAST-R is a water reducing, plasticizing and retarding concrete admixture, beneficial in maintaining workability especially in high ambient temperatures.

FEATURES

CAPLAST-R increases the dispersion of cement particles by combining the effects of a powerful plasticizing, de-flocculating and retarder blend. It enhances the dispersion of cement particles and wets them more thoroughly.

STANDARDS

CAPLAST-R complies with the specifications of ASTM C494 Type B and D as well as B.S. 5075 Part 1

USES

CAPLAST-R can be used:

- To increase the setting time of concrete and maintain its workability, especially in hot weather concreting, where delay to initial and final settings are important in addition to the maintenance of maximum slump.
- To reduce permeability, and thereby minimizing the effects of ground water salts on concrete and steel.
- To increase concrete strength at unchanged or improved workability.
- To increase concrete workability at unchanged or improved strength.
- To reduce cement content without loss of workability, and ultimate strength.

ADVANTAGES

- By using CAPLAST-R, setting time is retarded without reduction in strength. On the contrary, the retardation effect of CAPLAST-R is coupled with an ability to enhance concrete strength.
- By using CAPLAST-R water can be reduced to the extent of 8% to 15% according to sand grading, while retaining the same workability.

Strength can be improved by more than 20% through the reduction in the w/c ratio.

- By using CAPLAST-R, concrete workability can be improved. Slump will be increased by the addition of CAPLAST-R without reduction in water content. Concrete can be placed and compacted more easily without reduction in strength.
- By using CAPLAST-R, cement consumption can be reduced. Up to 10% of cement can be saved by taking advantage of water reduction, and still maintaining the desired concrete quality with unchanged workability.
- CAPLAST-R increases the placing time, hence larger batches can be achieved and placed. Even at higher ambient temperatures, concrete can be conveyed over greater distances without risk of setting.
- Improved surface finish, trowelability and pumpability of concrete.

TYPICAL PROPERTIES

Appearance:

Deep brown clear liquid.

Specific gravity:

About 1.15 at 25°C

Chloride content:

Nil to BS 5075

Air entrainment:

Complies with requirements of ASTM C 494 clause 12.2.1

Toxicity:

Non-toxic.

Compatibility with cement:

Compatible with all types of cement, except high alumina cement.

Compatibility with other admixtures:

Compatible with other Ahlia admixtures, provided they are added separately to the mix.

Shelf life:

At least 18 months if stored in tightly sealed containers at normal ambient temperature.

DIRECTIONS FOR USE

CAPLAST-R is supplied ready for use. It should be added to concrete mixes during mixing process preferably at the same time along with mix water.

Dosage:

Trials should be carried out to determine the optimum dosage of CAPLAST-R, taking into account the proposed mix design, performance requirements and site conditions.

As a general guide, a dosage range of 0.150 liter to 0.50 liter per 50 kg of cement is recommended as a starting point. Dosage outside recommended limit can be used by establishing the proper dosages on actual mix for required performance.

Dispensing:

Best by dispenser into the gauging water or directly with water into the mixer.

Overdosing:

An overdose of double the recommended dosage results in the following.

- Retardation of initial and final setting time.
- Increase in workability.
- Slight increase in air entrainment.

Provided if properly cured, the ultimate strength of concrete will not be adversely affected.

SAFETY PRECAUTIONS

CAPLAST-R is nontoxic and non-flammable. Splashes to eyes should be washed immediately with abundant water. It is advisable to use goggles and gloves while handling CAPLAST-R.

PACKAGING

CAPLAST-R is supplied in bulk (by arrangement), 205 liter barrels or 20 liter pails.

STORAGE

Preferably store in sealed conventional containers, protected from extreme weather conditions.

Rev-01 Feb-07

TECHNICAL SERVICE:

Our Technical Service Department is available at any time to advise you in the correct use of this product or any other Ahlia products.

Note : The information presented herein is based on the best of our knowledge and expertise for which every effort is made to ensure its reliability. Although all the products are subjected to rigid quality tests and are guaranteed against defective materials and manufacture, no specific guarantee can be extended because results depend not only on quality but also on other factors beyond our control.

As all Ahlia Technical Data Sheets are updated on a regular basis, it is the user responsibility to collect most recent issue.

ISO Certification