

INSUSOL (FG)



DESCRIPTION

INSUSOL (FG) is a Plastomeric Modified Bitumen Waterproofing Membrane manufactured in a superior calendaring process by saturating and coating a fiberglass fleece carrier with a waterproofing compound made of a special grade of modified bitumen with APP Polymers. Whereas the modifiers boost the thermal, mechanical and aging characteristics of the membrane compound; the Fiberglass fleece carrier establishes the mechanical characteristics as it performs as the reinforcement element that provides the membrane with its significant dimensional stability and moderate mechanical properties.

INSUSOL (FG) upper and lower faces are laminated with Thermo - Fusible Polyethylene film.

KEY FEATURES

- Outstanding performance with high temperature and good at low temperature.
- High dimensional stability due to Fiberglass characteristics.
- Absolute impermeability to water.
- Excellent adhesion to any surface.
- Excellent compatibility with modified and oxidized bitumen waterproofing systems.

APPLICATIONS

INSUSOL (FG) membranes are used for general waterproofing purposes in applications subject to limited mechanical stresses and as a base layer for a multi-layer waterproofing systems, and first layer in re-roofing works on substrates with modified membranes, and recommended for the subsequent applications:

- Base layer in multi-layer APP waterproofing systems.
- Damp-Proofing and wet areas.
- Inclined protected small roofs with limited reach.
- Re-roofing works on existing bitumen based waterproofing systems.

INSTALLATION

- INSUSOL (FG) membranes are installed by using propane torch welding as loose laid or fully bonded depending on the waterproofed system design requirements.
- The membrane rolls should be unloaded carefully without throwing.
- The substrate surface should be clean, dry, smooth and free from any irregularities & dust.
- According to the surface conditions; the surface might be in need for a cold applied bituminous primer layer before the membrane installation.
- The Modified Bitumen Waterproofing Membranes should be unrolled and placed in aligned position.
- Side overlap should be from 7 - 10 cm, while end overlap should be from 10 - 15 cm.
- For fully bonded systems, the membranes should be re-rolled without compromising its orientation while installation with propane torch and exposing the lower surface to the flame till the polyethylene film burns and the bituminous mass start melting, consequently creating a heat weld between the membrane and the substrate.
- For seams welding, torching takes place from above by heating the contact line at side & end overlaps then using a trowel to create pressure at the upper membrane to the lower one while avoiding long time flame exposure on the same point.
- For sloping roofs, the membrane should be laid from the lower edge with longitudinal direction of rolls perpendicular to slop direction, as the side lap of the consecutive roll should be placed above the prior one.

SURFACE FINISH

The lower and upper surfaces are laminated with Polyethylene film.

STORAGE

All Modified Bitumen Waterproofing Membrane should be stored in upright position in dry, flat, ventilated and away from direct sun light storage area.

DELIVERY INFORMATION

Thickness	mm	2,3,4
Roll Length	M	10
Roll Width	M	1

INSUSOL (FG)

APP Modified Bitumen Membrane With Glassfiber Reinforcement

TEST	MEASURING UNIT	TEST METHOD	INSUSOL إنسوسول	الإختبار
Thickness	mm	EN 1849-1	2, 3,4	السمك
Width	m	EN 1849-1	1	العرض
Length	m	EN 1849-1	10	الطول
Ortometry (5m Length Specimen)	mm	EN 1849-1	± 5	درجة إستواء السطح
Softening point (R&B)	°C	ASTM D- 36	150	درجة اللبونة
Penetration @ 25 °C	dmm	ASTM D- 5	15	درجة الإختراق عند ٢٥ مئوية
Penetration @ 60 °C	dmm	ASTM D- 5	70	درجة الإختراق عند ٦٠ مئوية
Tensile Strength (max)				مقاومة الشد القصوى
Longitudinal	N/5cm	ASTM D- 5147	400	طولياً
Transverse	N/5cm	ASTM D- 5147	250	عرضياً
Elongation @ Break				أقصى معدل للإستطالة
Longitudinal	%	ASTM D- 5147	≥2.5	طولياً
Transverse	%	ASTM D- 5147	≥2.5	عرضياً
Tearing Strength (Nail-Shank)				مقاومة التمزق
Longitudinal	N	EN 12310-1	70	طولياً
Transverse	N	EN 12310-1	80	عرضياً
Static Puncturing	-	UNI 8202/11	PS-2	مقاومة الإختراق الإستاتيكي
Dynamic Puncturing	-	UNI 8202/12	-	مقاومة الإختراق الديناميكي
Heat Flow	°C	ASTM D-5147, EN 1110	110	الثبات عند درجات الحرارة العالية
Cold Temperature Flexibility	°C	ASTM D-5147, EN 1109	0 to +3	المرونة عند درجات الحرارة المنخفضة
Dimensional Stability				ثبات الأبعاد
Longitudinal	%	EN 1107-1	Stable	طولياً
Transverse	%	EN 1107-1	Stable	عرضياً
Impermeability To Water	100 Kpa	EN 1928:2000	Absolute	مقاومة نفاذية المياه
Water Absorption	%	ASTM D-5147, UNI 8202/22	Less than 0.15	درجة إمتصاص الماء
Vapour Permeability	u	EN 1931	50,000	درجة نفاذية بخار الماء
Joints Tensile Strength	N/5cm	EN-12317, UNI 8202/30	Equal to membrane	مقاومة الشد عند مناطق التوصيل
Thermal Ageing in air (in oven at 70± 2°C)	-	EN 1296	4 weeks passed	الإهتراء نتيجة التسخين
Adhesion To Concrete (Torch Applied)	N/cm	EN 12316	20	قوة الإلتصاق بالأسطح الخرسانية

All International Industrial Rights Of This Product Have Been Reserved By INSUTECH



16765
Info@insutech-eg.com

www.insutech-eg.com