

## Sika Bond® -LA

### Water Resistant Bonding Agent

**Product Description** A synthetic rubber emulsion for adding to cementitious mixes where good adhesion and water resistance are required.  
Complies to ASTM C-1059-91

**Uses** Sika Bond® -LA is a high quality emulsion that substantially increases the qualities of cement mortars, such as:

- Thin layer patching mortars.
- Renders.
- Floor screeds.
- Concrete repairs.
- Abrasion resistant linings.
- Tile fixing mortars.
- Masonry mortars.
- Dust proffer.
- For Bonding of old to new concrete.

**Advantages** Sika Bond® -LA is a simply added to the mixing water to provide the following beneficial properties:

- Extremely good adhesion.
- Reduced shrinkage.
- Greater elasticity.
- Excellent water resistance.
- Increased abrasion resistance.
- Improved chemical resistance.
- Non -toxic.

N.B. Sika Bond® -LA does not re-emulsify, even in high alkaline conditions.

**Approval / Standards** Sika Bond® -LA has been tested as per SCAQMD Rule 1168.  
Result: VOC 0 g/l

#### Technical Data

**Type** Styrene Butadiene Liquid.

**Colour** White

**Density** 1.01 ± 0.01 kg/l.

**Packing** 5 kg and 20 kg pails  
200 kg Drums

**Storage Conditions** Free from heat and frost.

**Shelf life** 12 months when unopened. Store away from direct sun light

#### Application

##### Coverage

For general repair dilute with 1 to 2.5 parts of water.

As Bonding Agent – use pure or dilute 1 to 1 parts of water.

Consumption figures in the following table for Sika Bond® -LA in kg for m<sup>2</sup> per cm thickness (approx).

	Sika Bond® – L A : Water	1:1		1:2		1:3		1:4	
Cement :	1:1	2.3	3.0	1.5	2.1	1.1	1.5	0.9	1.2
	1:2	1.4	1.9	0.9	1.3	0.7	1.0	0.6	0.8
	1:3	1.1	1.5	0.7	1.0	0.5	0.8	0.4	0.6
	W/C Ratio	0.5	0.8	0.5	0.8	0.5	0.8	0.5	0.8



<b>Surface Preparation</b>	Concrete surfaces should be clean, sound and free from oil, grease, cement laitance and all loosely particles. Absorbent surfaces should be saturated thoroughly to surface saturated dry condition (S.S.D).
<b>Materials</b>	Aggregates should be well graded and thoroughly washed. Sand particle sizes should correspond to the thickness of mortar and concrete to be applied and required surface finish. Up to 2 mm thick 0-0.5 mm. 2 – 5 mm 0-1.0 mm 5 – 15 mm 0-3.5 mm Over 15 mm. 0-7.0 mm Over 35 mm 0-20 mm
<b>Application Guide Lines</b>	Sika Bond® -LA is a generally added to the clean mixing water within the range 1:1 – 1:2.5. For all applications apart from sprayed on renders a bonding coat of Sika Bond® -LA : water = 1:1 mixed with fresh cement should be brushed into the prepared surfaces. Subsequently mortar application must be carried out whilst the bonding coat is still wet. Add more Sika Bond® -LA solution if required
<b>Cleaning</b>	Clean all tools and equipment with clean water immediately after use.
<b>Important Recommendations</b>	<ul style="list-style-type: none"><li>■ Renderings floor toppings should be allowed to cure correctly. Protect the applied mortar and concrete from heat and frost exposure.</li><li>■ Avoid excessive air- entrainment through over mixing.</li><li>■ Do not use Sika Bond® -LA and water as a bonding agent - always add cement and sand.</li><li>■ Minimum application temperature + 5° C.</li></ul>
<b>Safety Instructions</b>	
<b>Ecology</b>	Do not dispose of into water or soil but according to local regulations.
<b>Transport</b>	Non-hazardous.
<b>Safety Precautions</b>	Contact with skin, eyes or mucous membrane may cause irritation flush with clean water, seek medical attention.
<b>Toxicity</b>	Non-Toxic under relevant health and safety codes.
<b>Legal notes</b>	The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



**Sika Egypt for Construction Chemicals**  
El About City  
1<sup>st</sup> industrial zone (A)  
Section # 10 Block 13035,  
Egypt

Tel :+202- 4481 0580  
Fax :+202- 4481 0459  
Mob :+2012- 2390 8822/55  
www.sika.com.eg

