## ALYAF A601 XL

Product Data Sheet -

**ALYAF A601 XL** is a nonwoven Geotextile made from staple fibers, mechanically bonded by a needle punching process to produce a dimensionally stable network. The fibers used are 100% white polyester, ultra-violet resistant with 256°C melting point. ALYAF Geotextiles are manufactured according to Quality System procedures that have been assessed and certified in accordance to EN ISO 9001:2008.

## **APPLICATION AREAS:**

					FILTRATION
ROADS	RAILWAYS	TUNNELS & UNDERGROUND STRUCTURES	EROSION CONTROL SYSTEMS	DRAINAGE	a
<b>•</b>	*	**			
CANALS	SOILD WASTE	LIQUID WASTE	RESERVOIRS & DAMS	FOUNDATION & RETAINING WALLS	PROTECTION

Properties	Test Method	Unit	Value
Tensile Strength CD	EN ISO 10319	kN/m	27
Tensile Strength MD	EN ISO 10319	kN/m	27
Elongation at break CD / MD	EN ISO 10319	%	65 / 55
CBR Puncture	EN ISO 12236	Ν	5000
Dynamic Puncture	EN ISO 13433	mm	6
Permeability	EN ISO 11058	10 <sup>-3</sup> ms <sup>-1</sup>	40
Flow rate normal to the plane	EN ISO 11058	l/m <sup>2</sup> /sec	40
Opening Size (O <sub>90</sub> )	EN ISO 12956	microns	67
Thickness under 2kPa	EN ISO 9863-1	mm	4.0
Mass Per Unit Area	EN ISO 9864	g/m²	500
Roll Width	nominal	meters	6
Roll Length	nominal	meters	100

Notes:

ALYAF geotextiles are non-biodegradable, have excellent resistance to chemicals and salts normally present in the soil and are unaffected by prolonged contact with hydrocarbon such as gasoline and deisel.

▶ ALYAF geotextiles have excellent UV resistance and exhibit strength retention of 70% on test for weathering resistance to EN 12224.

Values reported in this data sheet are the average results obtained in our laboratory and Independent testing institutions and are subject to manufacturing tolerances.

The property values listed above are effective September' 2014.

• Engineered grades to meet specific project requirements are available upon request.

Properties optimization and practical experience can make revisions necessary, the right is reserved to make changes without prior notice.

Corporate Member

International Geosynthetic Society

www.alyaf.com info@alyaf.com



Rev.04 September.'14 Geospec. A1 XL

س. ت ٢٠٥٠٠٢١٦٦٦ – ص. ب ١٠٧٣٧، الدمام ٣١٤٤٣ – المملكة العربية السعودية – تلفون: ١٣٨١٢ ١٢٨٦ ٢٩٦ + ( ٦ خطوط ) – فاكس: ١٣٨١٢ ١٢٨٦ ٢٦٦ C.R. 2050021660 - P.O. Box 10737 , Dammam 31443 - Kingdom of Saudi Arabia - Tel.: +966 13 812 1206 (6 Lines), Fax : +966 13 812 1836



SEPARATION

ركة الألياف الصناعية الحدودة 💵

<u>A1</u>XL Range

ALYAF INDUSTRIAL CO. LTD.