



ROWAD HDPE DOUBLE SMOOTH BLACK (HDS):

ROWAD HDPE Geomembranes are produced from prime quality, high molecular weight resins and are specially designed for most containment and environmental protection applications. The finished product has exceptional mechanical and chemical resistance properties, is highly durable with excellent aging, UV resistance and Environmental Stress Crack Resistance properties making it very suitable for most exposed applications. ROWAD Geomembranes are produced with virgin resins and DO NOT contains any fillers, foreign additives or plasticizing agents.

The ROWAD Geomembrane specification shown below meets or exceeds customer specification.

| Tested Prosperities | Test Method | Frequency | HDS 0.75 mm | HDS 1.00 mm | HDS 1.50 mm | HDS 2.00 mm | HDS 2.50 mm | HDS 3.00 mm | | | | | | |
|---|----------------------------|--------------------|----------------|----------------|----------------|----------------|----------------|----------------|-----|-----|-----|-----|-----|-----|
| Thickness, (Nominal) mm | ASTM D 5199 | Per roll | 0.75 | 1.00 | 1.50 | 2.00 | 2.50 | 3.00 | | | | | | |
| Density(min ave), g/cm ³ | ASTM D 792 | 90,000 Kgs | 0.940 | 0.940 | 0.940 | 0.940 | 0.940 | 0.940 | | | | | | |
| Tensile Properties , (min. ave) | ASTM D 6693, Type IV | 9,000 Kgs | | | | | | | | | | | | |
| Strength at Yield , N/mm | 50mm /min | | | | | | | | 11 | 15 | 22 | 29 | 37 | 44 |
| Strength at Break, N/mm | G.L. = 33 mm | | | | | | | | 20 | 27 | 40 | 53 | 67 | 80 |
| Elongation at Yield, % | G.L. = 50 mm | | | | | | | | 12 | 12 | 12 | 12 | 12 | 12 |
| Elongation at Break, % | | | | | | | | | 700 | 700 | 700 | 700 | 700 | 700 |
| Tear Resistance,(min ave) N | ASTM D 1004 | 20,000 Kgs | 93 | 125 | 187 | 249 | 311 | 374 | | | | | | |
| Puncture Resistance,(min ave) N | ASTM D 4833 | 20,000 Kgs | 240 | 320 | 480 | 640 | 800 | 960 | | | | | | |
| Carbon Black Content, (range) % | ASTM D1603/4218 | 9,000 Kgs | 2.0 - 3.0 | 2.0 - 3.0 | 2.0 - 3.0 | 2.0 - 3.0 | 2.0 - 3.0 | 2.0 - 3.0 | | | | | | |
| Carbon Black Dispersion | ASTM D 5596 | 20,000 Kgs | +Note 1 | +Note 1 | +Note1 | +Note 1 | +Note 1 | +Note 1 | | | | | | |
| Notched Constant Tensile Load, hrs | ASTM D 5397 | Per GRIGM10 | 500 | 500 | 500 | 500 | 500 | 500 | | | | | | |
| Oxidative Induction Time, mins | ASTM D 3895 | 90,000 Kgs | 100 | 100 | 100 | 100 | 100 | 100 | | | | | | |
| Dimensional Stability, % | ASTM D 1204 | Resin batch | ±1 | ±1 | ±1 | ±1 | ±1 | ±1 | | | | | | |
| Oven Aging at 85°C HP OIT % retained after 90 days | ASTM D 5721 ASTM D 5885 | Per formulation | >80 | >80 | >80 | >80 | >80 | >80 | | | | | | |
| UV Resistance HP OIT % retained after 1600 hrs | GM 11 ASTM D 5885 | Per formulation | >50 | >50 | >50 | >50 | >50 | >50 | | | | | | |
| Width(m) - BF / FD | RTM | Per Roll | 8 / 8 | 8 / 8 | 8 / 8 | N.A / 8 | N.A / 8 | N.A / 8 | | | | | | |
| Length(m) - BF / FD | RTM | Per Roll | 225 / 225 | 170 / 170 | 110 / 110 | N.A / 80 | N.A / 70 | N.A / 50 | | | | | | |
| Area (m ²) - BF / FD | RTM | Per Roll | 1800 | 1360 | 880 | 640 | N.A / 560 | N.A / 400 | | | | | | |

NOTES:

- 1: Carbon black Dispersion only applies to near spherical agglomerates. 10 of 10 views in Category 1 or 2.
- 2: Testing frequencies are rounded the nearest full roll.
- 3: Roll lengths & widths have a tolerance of ±1%.
- 4: NCTL/OIT Results for Smooth and Textured materials (BF) are taken from SMOOTH Section/Selvedge of the Role & All 3rd Party Tests Must be taken from this section only, however for all ETEX the OIT test can be taken anywhere on the Sheet.
- 5: Where offered, Conductive layers will be complete across the bottom of each roll. (Conductive Sheets will BF only).
- 6: For reference; BF= Blown Film, FD= Flat Die.
- 7: Where offered single Textured rolls, will be located on the upper face Unless otherwise agreed.
- 8: The minimum average thickness value is equal Nominal Thickness – 5%.

FM:120,Rev:08 (Oct 2017)



A TASNEE التسنيع COMPANY

For more information, please contact:
Rowad International Geosynthetics Co. Ltd. | Street 42, Second Industrial City | P.O. Box 14164 | Dammam 31424 | Kingdom of Saudi Arabia
T: +966 13 8121360 | W: www.rowadplastic.com